



TECHNICAL DATA SHEET – AS-250

Revised: 5/2018

PRODUCT DESCRIPTION

AS-250 is a general purpose, vehicular grade, non-slip deck coating designed for application in slippery areas to make them safer for operations of foot and rolling equipment traffic.

AS-250 was originally developed for application on flight decks of aircraft carriers to provide the greatest possible resistance to wear and tenaciously adhere to decks so as not to fracture or disintegrate under the impact of high speed aircraft landings.

AS-250 resists most acids, alkalis, solvents, grease, oil, salt water, detergents, alcohol, gasoline, jet fuels, and hydraulic fluids. Refer to American Safety Technologies Chemical Resistance Table for detailed performance data.

SURFACE PREPARATION

CONCRETE: Remove oil, grease, dirt, wax, etc., by dissolving with a commercial grade cleaner/degreaser then flush the area thoroughly with clean water and allow it to dry. Remove all paint films, laitance, and loose concrete by scarification or shot blasting. Patch any holes or significant defects with PolySpec® RezRok 105 Patching Compound. Smooth or glazed surfaces should be roughened and new concrete should cure at least 30 days with good ventilation prior to application. Form release agents, hardeners, sealer, etc. will interfere with adhesion and must be removed. Prime the surface with PS-100 WB Water-based Primer.

METAL: All surfaces must be clean, dry, and free of surface contamination. Remove all deposits of oil and grease using Solvent Cleaning method SP-1. Next, the surface must be mechanically blasted to a NACE 2, Near White Metal blast with a 2-4 mil anchor profile ensuring that previous coatings, rust, and mil scale (if any) are thoroughly removed. Blasted surfaces should be primed immediately with MS-7CZ Industrial Primer at 2-4 mils WFT.

WOOD/FIBERGLASS: A clean sound surface is required. Remove any dirt or oils from the surfaces with a commercial cleaner/degreaser and allow the surface to dry. Follow with sanding to remove loose or deteriorated surface and to obtain the proper surface profile. For wood prime the surface with PS-100 WB Water-based Primer. For fiberglass use the MS-7CZ Industrial Primer for the best adhesion.

AS-250

NON-SLIP FLOOR AND DECK COATING

APPLICATION TECHNIQUES

AS-250 is designed to be applied over a primer or sealer.

1. Thoroughly pre-mix base component with a mechanical mixer such as a pneumatic drill motor with a Jiffy® mixing blade making sure all settlement is lifted off the bottom of the container and is uniformly dispersed and assumes a uniform color and appearance.
2. Pour entire contents of hardener can into base material. Mix hardener and base material with a Jiffy® mixing blade for approximately 3-5 minutes scraping bottom and side of the can until mixed material assumes a uniform color and appearance. No induction time is required.
3. **AS-250** should be applied at surface temperatures between 50°F and 130°F and applications outside that range are not recommended.
4. Exterior applications must be protected from rain for at least 12 to 24 hours after application according to humidity. Protect from heavy or extended exposure to water, oil and chemicals for 5 to 7 days.

ROLLER: Rolled applications provide the most aggressive non-slip characteristics with an irregular, ridged profile.

5. Using a phenolic core roller it is important that the rolled profile expose the maximum amount of non-slip aggregate. If the aggregate is not properly exposed the coating may become slippery when wet.
6. Pour a ribbon of **AS-250** on the surface approximately 2' long and 6" wide. Roll material in one direction only, in slow straight strokes pulling material toward you with a moderate amount of pressure. Do not over-roll too many times or press down too heavily. Be careful that material does not build up too thickly along welds. Material applied too thickly may not properly cure.

TROWEL: Trowel applications provide excellent non-slip characteristics with a rough, textured surface.

1. Use a flexible bladed plasterer's finishing trowel approximately 4 inches by 12 inches. Use smooth edges, not notched.
2. Pour a ribbon of **AS-250** on the surface approximately 2' long & 6" wide.
3. Hold trowel at 45° angle to surface and spread with sweeping motion. Reverse angle of trowel for opposite stroke. Pull material toward you. Trowel across welds to avoid too thick an application.

SPRAY: Sprayed applications will result in a uniform appearance with good non-slip characteristics.

1. **AS-250** should not be thinned. Thinning could result in grit not remaining properly in suspension.
2. Specialized mastic type spray equipment is required. A recommended set-up is as follows:
 - a. A 5-gallon bottom outlet pressure tank equipped with double regulator and an air driven agitator, and 1" I.D. outlet pipe.
 - b. 25 feet of 3/8" air hose with 3/8" female connectors at each end.

- c. 25 feet of 3/4" material hose with 3/4" female connectors at each end.
 - d. A Binks® Model 7E2 spray gun equipped with 1/4" (#45) fluid nozzle and a 1/4" internal air cap or a Binks® Model 52-2012 (4 foot) pole gun equipped with the same fluid nozzle and air nozzle.
3. Minimum air supply required is 20 CFM at 90 lbs. pressure. Recommended pressure is 15-20 psi on material and 20-25 psi on atomization. Always keep atomization air pressure higher than pot pressure with constant agitation. Good coverage and film thickness will be obtained working at 18" - 24" from surface. Overlap strokes about 50%. Make sure of wet application. Very little abrasive rebound will be noticed at 15 psi; however, it will be more noticeable at higher pressures.
 4. When temperature is above 80°F, it is advisable to flush the spray equipment with epoxy solvents every hour or so in order to prevent the possibility of any material setting up and plugging the equipment.

SURFACE MAINTENANCE

Maintain a clean surface to ensure the anti-slip performance of the **AS-250** is maximized. The following cleaning procedure is recommended.

1. Foreign matter such as chewing gum should be removed with a scraper or putty knife. Then apply an all-purpose, biodegradable cleaner/degreaser that can be mixed with water to the surface.
2. Scrub surface with a long-handled, fiber bristled brush or floor machine.
3. Rinse with clean water and dry.

Although extremely durable, **AS-250** is not a permanent coating and will require occasional touch up, especially in heavy traffic areas.

PRODUCT SPECIFICATIONS

V.O.C	2.07 lbs. per gal. (250 grams/liter)
VOLUME SOLIDS - %	71%
POT LIFE	4 hours @ 70°F (21°C)
DRY TIME	Light Traffic - 12 hours @ 70°F (21°C) Heavy Traffic - 72 hours @ 70°F (21°C)
ESTIMATED COVERAGE	60 sq. ft. per gallon – spray 50 sq. ft. per gal. – trowel 40 sq. ft. per gal. – roller
WEIGHT PER GALLON	14.9 lbs. per gal. (1.80 kg./liter)
FLASH POINT	81°F (27°C) - CC
COEFFICIENT OF FRICTION ASTM F609	Dry - 1.05 Wet - 1.05
PACKAGING	1 gallon kits 5 gallon kits
SHELF-LIFE	2 years in unopened container
STANDARD COLORS	Black, Gray, Haze Gray, Tile Red and Safety Yellow

CAUTION: Read Safety Data Sheet before using this material. Use only with adequate cross ventilation. Keep away from extreme heat, sparks and open flame. Keep from freezing. Avoid prolonged breathing of vapors. For dizziness, seek fresh air. Avoid contact with skin. Use gloves, goggles and coveralls. In case of spillage on clothing, change clothing to prevent prolonged contact with skin. Wash contaminated clothing before reuse. In case of accidental contact with skin, wash immediately with soap and water. In case of eye contact, flush thoroughly with plenty of water and call physician. If swallowed accidentally, do not induce vomiting. Seek medical attention immediately. The user of this product is responsible for making its own evaluation and tests regarding the capabilities, safety, utility, suitability and application of the product, and assumes all risks and liabilities resulting from the use or application of the product, whether used alone or with other products. ITW Polymers Sealants North America, Inc. (herein referenced to as the COMPANY) warrants only that the product conforms to the specifications contained in product Technical Data Sheets published By the COMPANY, a copy of which is available to the user. If the product fails to conform to this warranty, the user shall return the product within 10 days of the purchase date with a note specifying the defect and the COMPANY will either replace the product or at its option, return the purchase price. EXCEPT AS EXPRESSLY PROVIDED IN THIS PARAGRAPH, THE COMPANY MAKES NO REPRESENTATIONS OR WARRANTIES OF ANY KIND, NATURE OR DESCRIPTION, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, AND HEREBY DISCLAIMS THE SAME. In no event shall the COMPANY be liable to the user of this product, whether in contract or in tort or any other legal theory (including, without limitation, negligence), for damages which exceed the purchase price of the product, or for any indirect, incidental, consequential or similar damages, arising out of sale, use or application of the product, or for any claim made against the user by any other party, even if ITW Polymers Sealants North America, Inc. has been advised of the possibility of such claim.