



## TECHNICAL DATA SHEET – AS-150 HAPS FREE

Revised: 5/2018

### PRODUCT DESCRIPTION

**AS-150 HAPS Free** is a single-component, epoxy ester, anti-slip floor and deck coating designed for application in areas of heavy pedestrian grade traffic. This VOC compliant safety coating is both easy and fast to apply and offers optimum adhesion to metal, concrete and wood surfaces. The HAPS Free formulation meets VOC requirements for all 50 States including the South Coast Air Quality Management District (SCAQMD) of California. As part of ITW Polymers Sealants North America, Inc.'s commitment to preserve natural resources the **AS-150** contains a significant amount of unique sustainable/renewable ingredients in its formulation. **AS-150 HAPS Free** resists gasoline, oil, acids, alkalis, and aliphatic solvents. Refer to American Safety Technologies Chemical Resistance Table for detailed performance data.

### SURFACE PREPARATION

**CONCRETE:** Remove oil, grease, dirt, wax, etc., by dissolving with a commercial grade cleaner/degreaser then flush the area thoroughly with clean water and allow it to dry. Remove all paint films, laitance, and loose concrete by scarification or shot blasting. Patch any holes or significant defects with PolySpec® RezRok 105 Patching Compound. Smooth or glazed surfaces should be roughened and new concrete should cure at least 30 days with good ventilation prior to application. Form release agents, hardeners, sealer, etc... will interfere with adhesion and must be removed. Prime the surface with PolySpec 100EX.

**METAL:** All surfaces must be clean, dry, and free of surface contamination. Remove all deposits of oil and grease using Solvent Cleaning method SP-1. Next, the surface must be mechanically blasted to a NACE 2, Near White Metal blast with a 2-4 mil anchor profile ensuring that previous coatings, rust, and mill scale (if any) are thoroughly removed. Blasted

surfaces should be primed immediately with MS-7CZ Industrial Primer at 2-4 mils WFT.

**WOOD/FIBERGLASS:** A clean sound surface is required. Remove any dirt or oils from the surfaces with a commercial cleaner/degreaser and allow the surface to dry. Follow with sanding to remove loose or deteriorated surface and to obtain the proper surface profile. For wood prime the surface with PolySpec 100EX. For fiberglass use the MS-7CZ Industrial Primer for the best adhesion.

### APPLICATION TECHNIQUES

**AS-150 HAPS Free** coating is designed to be applied over a primer or sealer.

1. Thoroughly mix contents preferably with a mechanical mixer such as a pneumatic drill motor with a Jiffy® mixing blade until mixed material assumes a uniform color and appearance.
2. **AS-150 HAPS Free** should be applied at surface temperatures between 50°F and 120°F and applications outside that range are not recommended. Below 50°F, curing time will increase substantially.
3. Exterior applications must be protected from rain for at least 24 hours after application according to humidity. Protect from heavy or extended exposure to water, oil and chemicals for 5 to 7 days.

**ROLLER:** Provides aggressive anti-slip characteristics with an irregular, ridged profile.

1. Use a phenolic core roller. It is important that the rolled profile expose the maximum amount of anti-slip aggregate. If aggregate is not properly exposed, the coating may become slippery when wet.
2. Pour a "ribbon" of **AS-150 HAPS Free** coating on the surface approximately 2' long and 6" wide. Roll material in one direction only, in slow straight strokes pulling material toward you with a moderate

# AS-150 HAPS FREE

SINGLE-COMPONENT, ANTI-SLIP COATING  
CONTAINS KEVLAR PAT. NO. 5,686507

amount of pressure. Do not over-roll too many times or press down too heavily. Be careful that material does not build up too thickly along welds (roll across welds, not along them). Material applied too thick may not properly cure.

**TROWEL APPLICATION:** (Provides excellent anti-slip characteristics with a rough, textured surface)

1. Use a smooth edged flexible plasterer's finishing trowel approximately 4 inches by 12 inches.
2. Pour a "ribbon" of **AS-150 HAPS Free** coating on the surface approximately 2' long and 6" wide.
3. Hold trowel at 45° angle to surface and spread with sweeping motion. Pull material toward you. To cover corners, etc., pull straight strokes using material on the trowel. Trowel across welds to avoid too thick an application.

**SPRAY APPLICATION** (Gives a uniform appearance with good anti-slip characteristics)

1. **AS-150 HAPS Free** coating should not be thinned.
2. Specialized mastic type spray equipment is required. A recommended set-up is as follows:
  - a. A 5-gallon bottom outlet pressure tank equipped with a double regulator and an air driven agitator, and 1" I.D. outlet pipe.
  - b. 25 feet of 3/8" air hose with 3/8" female connectors at each end.
  - c. 25 feet of 3/4" material hose with 3/4" female connectors at each end.
  - d. A Binks Model 7E2 spray gun equipped with 1/4" (#45) fluid nozzle and a 1/4" internal air cap or a Binks Model 52-2012 (4 foot) pole gun equipped with the same fluid nozzle and air nozzle.
3. Minimum air supply required is 20 CFM at 90 lbs. pressure. Recommended pressure is 15-20 psi on material and 20-25 psi on atomization. Always keep atomization air pressure higher than pot pressure with constant agitation. Good coverage and film thickness will be obtained working at 18" or 24" distance from surface. Overlap strokes about 50%. Make sure of wet application. Very little abrasive rebound will be noticed at 15 psi; however, it will be more noticeable at higher pressures.

### SURFACE MAINTENANCE

Maintain a clean surface to ensure the anti-slip performance of the **AS-150 HAPS Free** is maximized. The following cleaning procedure is recommended.

1. Foreign matter such as chewing gum should be removed with a scraper or putty knife. Then apply an all-purpose, biodegradable cleaner/degreaser that can be mixed with water to the surface.
2. Scrub surface with a long-handled, fiber bristled brush or floor machine.
3. Rinse with clean water and dry.

Although extremely durable, **AS-150 HAPS Free** is not a permanent coating and will require occasional touch up, especially in heavy traffic areas.

### PRODUCT SPECIFICATIONS

V.O.C	0.82 lbs. per gallon (98 grams/liter)
VOLUME SOLIDS - %	61%
DRY TIME	Light Traffic - 12 hours @ 70°F (21°C) Heavy Traffic - 72 hours @ 70°F (21°C)
ESTIMATED COVERAGE	60 sq. ft. per gallon – spray 40 sq. ft. per gallon – trowel 50 sq. ft. per gallon – roller
WEIGHT PER GALLON	14.8 lbs. per gal. (1.77 kg./liter)
FLASH POINT	102°F (39°C) - CC
COEFFICIENT OF FRICTION ASTM F609	Dry - 1.17 Wet - 1.00
PACKAGING	1 gallon kits 5 gallon kits
SHELF-LIFE	2 years in unopened container
STANDARD COLORS	Black, Gray, Safety Yellow, Neutral Tint Base and White Tint Base

### APPLICATION NOTES

Only use an approved tinting system and pigment when adding colorants. The white tint base should receive no more than 8 fluid oz. of tint and the neutral base 12 fluid oz. high amount of colorants can affect viscosity, cure time and ultimate strength of the product. After colorant has been added, material must be shaken for a minimum of 5 minutes to blend in pigment. Premixing with a drill prior to application is also recommended. A test area should be applied so color and appearance can be verified. Deep color may require additional cost to hide.

**CAUTION:** Read Safety Data Sheet before using this material. Use only with adequate cross ventilation. Keep away from extreme heat, sparks and open flame. Keep from freezing. Avoid prolonged breathing of vapors. For dizziness, seek fresh air. Avoid contact with skin. Use gloves, goggles and coveralls. In case of spillage on clothing, change clothing to prevent prolonged contact with skin. Wash contaminated clothing before reuse. In case of accidental contact with skin, wash immediately with soap and water. In case of eye contact, flush thoroughly with plenty of water and call physician. If swallowed accidentally, do not induce vomiting. Seek medical attention immediately. The user of this product is responsible for making its own evaluation and tests regarding the capabilities, safety, utility, suitability and application of the product, and assumes all risks and liabilities resulting from the use or application of the product, whether used alone or with other products. ITW Polymers Sealants North America, Inc. (herein referenced to as the COMPANY) warrants only that the product conforms to the specifications contained in product Technical Data Sheets published By the COMPANY, a copy of which is available to the user. If the product fails to conform to this warranty, the user shall return the product within 10 days of the purchase date with a note specifying the defect and the COMPANY will either replace the product or at its option, return the purchase price. EXCEPT AS EXPRESSLY PROVIDED IN THIS PARAGRAPH, THE COMPANY MAKES NO REPRESENTATIONS OR WARRANTIES OF ANY KIND, NATURE OR DESCRIPTION, EXPRESS OR IMPLIED, INCLUDING, WITHOUT LIMITATION, ANY WARRANTY OF MERCHANTABILITY OR FITNESS FOR ANY PARTICULAR PURPOSE, AND HEREBY DISCLAIMS THE SAME. In no event shall the COMPANY be liable to the user of this product, whether in contract or in tort or any other legal theory (including, without limitation, negligence), for damages which exceed the purchase price of the product, or for any indirect, incidental, consequential or similar damages, arising out of sale, use or application of the product, or for any claim made against the user by any other party, even if ITW Polymers Sealants North America, Inc. has been advised of the possibility of such claim.